

# TEST REPORT

**APPLICANT** : CROMOLOGY, S.L.

**ADDRESS** : C/ Francia,7 P.I. Pla De Llerona  
08520 Les Franqueses Del Valles  
At. Sra. Luisa Arreondo

**SAMPLE DESCRIPTION** : 797208 - 2034001 IMPERTRESA ELASTICO  
BLANCO/BASE BLANCA Líquido II - MUESTRA

**PURCHASE ORDER NO.** : POKQ201371

**REPORT NO.** : 1207179

**FILE NO.** : 784276

**SAMPLE RECEIVED DATE** : 09-Dec-2020

**TURN AROUND TIME** : 09-Dec-2020 to 16-Dec-2020

The following test item(s) was/were performed on submitted sample(s) and/or component(s) confirmed by applicant

TEST REQUESTED	TEST METHOD/REGULATION	RESULT
Migration of Certain Elements	EN71 Part 3:2019, Directive (EU) 2019/1922	Pass

*Samples are obtained by express delivery, Results obtained refer only to samples, products or material received in Laboratory, as described in point related to sample description, and tested in conditions shown in present report. Eurofins Product Testing Service (Shanghai) Co., Ltd ensures that this job has been performed according to our Quality System and complying contract and legal conditions. If you happen to have any comments, please do it by sending email to [info.sh@eurofins.com](mailto:info.sh@eurofins.com) and referring to this report number. Reproduction of this document is only valid if it is done completely and under the written permission of Eurofins Product Testing Service (Shanghai) Co., Ltd. If you happen to have any complaints, please do it by sending email to [chinacomplaint@eurofins.com](mailto:chinacomplaint@eurofins.com) and referring to this report number.*

**Eurofins (Shanghai) contact information****Customer service: [SammyCao@eurofins.com](mailto:SammyCao@eurofins.com) / 021-36202855**

\*\*\*\*\* FOR FURTHER DETAILS, PLEASE REFER TO THE FOLLOWING PAGE(S) \*\*\*\*\*


Signed for and on behalf of  
Eurofins Product Testing Service (Shanghai) Co., Ltd



---

Jackson Zhou  
Chemical Lab Manager

**SAMPLE PHOTO(S)**



**EFSH20120864-CG-01**

\*\*\*TO BE CONTINUED\*\*\*

## COMPONENT LIST

Component No.	Component	Sample No.
1	White paint	A

\*\*\*TO BE CONTINUED\*\*\*

## TEST RESULT

### Migration of Certain Elements

Test Request: Migration of certain elements as specified in Part III of Annex II to Toy Safety Directive 2009/48/EC and its amendment Directive (EU) 2019/1922.

Test Method: General elements, with reference to EN 71 Part 3:2019, analysis was performed by ICP-MS; Extractable Chromium (VI), with reference to EN 71 Part 3:2019, analysis was performed by IC-ICP-MS / IC-UV/VIS; Extractable organic tin, with reference to EN 71 Part 3:2019, analysis was performed by GC-MS.

Test Item(s):	Unit	Result
		1
Category Type		II
Extractable Lead (Pb)	mg/kg	ND
Extractable Antimony (Sb)	mg/kg	ND
Extractable Arsenic (As)	mg/kg	ND
Extractable Barium (Ba)	mg/kg	ND
Extractable Cadmium (Cd)	mg/kg	ND
Extractable Mercury (Hg)	mg/kg	ND
Extractable Selenium (Se)	mg/kg	ND
Extractable Boron (B)	mg/kg	ND
Extractable Cobalt (Co)	mg/kg	ND
Extractable Manganese (Mn)	mg/kg	ND
Extractable Strontium (Sr)	mg/kg	ND
Extractable Zinc (Zn)	mg/kg	71
Extractable Copper (Cu)	mg/kg	ND
Extractable Aluminum (Al)	mg/kg	534
Extractable Nickel (Ni)	mg/kg	ND
Extractable Tin (Sn)	mg/kg	ND
Extractable Organic Tin#1	mg/kg	ND
Extractable Chromium#2	mg/kg	ND
Extractable Chromium (III) (Cr III)#3	mg/kg	-
Extractable Chromium (VI) (Cr VI)	mg/kg	-

#### Note:

- #1 - Result of Organic Tin is calculated by assuming the extractable Tin content is wholly contributed from tributyltin (TBT) cation unless further specified.
- #2 - If the migration of total Chromium is below the maximum limit for Chromium (VI), it can be inferred that the material complies with the requirements for both Chromium(III) and Chromium(VI).
- #3 - In particular Chromium (III) is calculated by subtracting the Chromium (VI) concentration from the total chromium concentration.

#### Remarks:

mg/kg = milligram per kilogram  
 MDL = Method Detection Limit  
 ND = Not Detected, less than MDL

\*\*\*TO BE CONTINUED\*\*\*

## TEST RESULT

Limits –MDL per category type:

Test Item(s):	Unit	Limit	MDL	Limit	MDL	Limit	MDL
Category Type		I		II		III	
Extractable Lead (Pb)	mg/kg	2.0	1.0	0.5	0.2	23	10
Extractable Antimony (Sb)	mg/kg	45	5	11.3	1	560	10
Extractable Arsenic (As)	mg/kg	3.8	0.2	0.9	0.1	47	5
Extractable Barium (Ba)	mg/kg	1500	50	375	10	18750	50
Extractable Cadmium (Cd)	mg/kg	1.3	0.1	0.3	0.05	17	1
Extractable Mercury (Hg)	mg/kg	7.5	0.5	1.9	0.2	94	10
Extractable Selenium (Se)	mg/kg	37.5	2	9.4	1	460	10
Extractable Boron (B)	mg/kg	1200	50	300	10	15000	50
Extractable Cobalt (Co)	mg/kg	10.5	1	2.6	0.2	130	10
Extractable Manganese (Mn)	mg/kg	1200	50	300	10	15000	50
Extractable Strontium (Sr)	mg/kg	4500	50	1125	50	56000	50
Extractable Zinc (Zn)	mg/kg	3750	50	938	50	46000	50
Extractable Copper (Cu)	mg/kg	622.5	10	156	10	7700	50
Extractable Aluminum (Al)*	mg/kg	2250	50	560	50	28130	50
Extractable Nickel (Ni)	mg/kg	75	5	18.8	2	930	10
Extractable Tin (Sn)	mg/kg	15000	50	3750	50	180000	50
Extractable Organic Tin	mg/kg	0.9	0.2	0.2	0.2	12	0.2
Extractable Chromium	mg/kg	-	0.02	-	0.005	-	0.02
Extractable Chromium (III) (Cr III)	mg/kg	37.5	2	9.4	1	460	10
Extractable Chromium (VI) (Cr VI)	mg/kg	0.02	0.02	0.005	0.005	0.053	0.02

Category I: dry, brittle, powder-like or pliable toy material

Category II: liquid or sticky toy material

Category III: scrapped-off toy material

"-" = Not Regulated

\* - The migration limit for Aluminum (Al) has been amended by Commission Directive (EU) 2019/1922. The new limits shall apply from 20 May 2021.

\*\*\*END OF THE REPORT\*\*\*